

Please Note: All screen inks can be ordered by phone or email. No shopping Cart on these items.



UV INKS - (BF) ULTRABOND SERIES

PRODUCT DESCRIPTION

BF ULTRABOND is a multipurpose UV screen ink for banner and electrostatic film applications. **BF ULTRABOND** is unique in its ability to adhere to highly plasticized vinyl banner, polyethylene banners and electrostatic vinyl films. **BF ULTRABOND**'s wide adhesion range is unmatched by all other UV 'banner' inks known to be on the market today. This provides screen printers with the opportunity to stock a single ink line for all banner applications.

SUBSTRATES

BF ULTRABOND exhibits excellent adhesion to vinyl banners, electrostatic film and polyethylene banner material having treatment levels of at least 40 dynes. It also provides good adhesion to pressure sensitive vinyl, bus king vinyl, polystyrene, ABS, standard and polyethylene card stock. High density and fluted polyethylene with use of 3-5% 1534 Adhesion Promoter.

CAUTION It is the Printer's Responsibility to Test Ink Before Printing	1. Allow 24-96 hours after test printing to evaluate ink for intended application.
	2. If product requires overlapping coats (i.e. multi-colours) test ink on substrate with overlapping coats.
	3. Refer to M.S.D.S. for heavy metal content.

BF ULTRABOND STANDARD COLOURS

Special Match Colors also available

CODE #	DESCRIPTION	3.78
BF-0101	Primrose Yellow	199.76
BF-0111	Lemon Yellow	188.59
BF-0123	Medium Yellow	181.21
BF-0131	Brilliant Orange	225.20
BF-0135	Vivid Orange	221.71
BF-0141	Fire Red	205.09
BF-0151	Scarlet Red	228.78
BF-0155	Rubine Red	227.71
BF-0160	Rhodamine Red	225.51
BF-0180	Warm Red	225.06
BF-0190	Process Blue	193.07
BF-0200	Peacock Blue	194.56
BF-0205	Reflex Blue	207.39
BF-0210	Ultra Blue	203.21
BF-0220	Emerald Green	187.28
BF-0225	Forest Green	205.25

CODE #	DESCRIPTION	3.78
BF-0226	Lime Green	202.04
BF-0235	Teal	192.65
BF-0240	Purple	212.72
BF-0260	Brown	221.97
BF-0301	Opaque Black	175.52
BF-0311	Opaque White	170.15
BF-0312	Dense Black	175.00
BF-0112	Tinting White	179.24
BF-0110	Shading Black	170.69
BF-1700	Mixing Clear	174.50
BF-1710	Metallic Mixing Clear	196.65
BF-1350	Overprint Clear	174.50
BF-1330	HT Yellow	220.10
BF-1630	HT Magenta	218.39
BF-1530	HT Cyan	171.01
BF-1130	HT Black	167.50

CODE #	DESCRIPTION	3.78
BF-1730	HT Base	178.12
BF-1333	HT Yellow PR	210.41
BF-1633	HT Magenta PR	209.62
BF-1533	HT Cyan PR	157.17
BF-1133	HT Black PR	167.50
BF-0064	CMS Yellow GS	211.85
BF-0066	CMS Yellow RS	235.15
BF-0114	CMS Orange	252.29
BF-0121	CMS Red YS	215.99
BF-0127	CMS Violet	219.48
BF-0164	CMS Red BS	209.60
BF-0165	CMS Magenta	218.62
BF-0230	CMS Blue	177.33
BF-0325	CMS Green	190.25
BF-1800	Thinner	126.00

FULL TECHNICAL SHEET AVAILABLE FOLLOWS BELOW

ULTRABOND BF PRODUCT DATA SHEET

Ultrabond BF is distinct in its ability to offer non-blocking and flexibility needed for banner applications while also providing adhesion to many point-of-purchase stocks. This versatility provides screen printers an opportunity to reduce ink inventory by stocking a single ink line for most applications. Ultrabond BF's exceptional flexibility and adhesion will stand up to the demand of the most stringent finishing requirements. Ultrabond BF provides a durable, non-blocking surface and has excellent outdoor durability.

PERFORMANCE PROPERTIES

- ➔ Broadest adhesion range of any Inktech/Polymeric UV ink
- ➔ Flexible for sewing, grommeting and die-cutting without cracking
- ➔ Allows double face printing without re-wetting or picking
- ➔ Superior opacity provides better color trapping
- ➔ Low tack finish to eliminate slip sheeting
- ➔ Water and abrasion resistance
- ➔ NVP and heavy metal free

RECOMMENDED SUBSTRATES

- ➔ Vinyl and Polyethylene Banner
- ➔ Electrostatic Vinyl
- ➔ Pressure sensitive vinyls
- ➔ Unsupported Vinyl
- ➔ Polystyrene
- ➔ ABS
- ➔ PETG
- ➔ Tyvek
- ➔ Many Coated Metals
- ➔ *Fluted Polyolefins (with BF-1534)
- ➔ Card Stock and Paper
- ➔ Print Treated Polyester
- ➔ Expanded Foam PVC
- ➔ Polycarbonate (without adhesives)

*A minimum of 40 Dynes of surface energy is recommended for Polyolefin stock.

CURING SPECIFICATIONS

Ultrabond BF will cure well when printed through 355 plain weave polyester mesh or finer. Ultrabond BF's optimal cure window of 125 – 160 mJ / 550 – 650 mW is generally achieved with one 200 watt per inch mercury vapor lamp at belt speeds between 75 - 100 feet per minute. Cure speeds may vary as thicker gauge stocks and dark surface colors require more energy. Adhesion should be a minimum of 95% from curing unit with final adhesion developing within four hours of initial polymerization. Coarser fabrics can be utilized; however, curing parameters may need to be adjusted for the increased ink film. If a loss of gloss or adhesion due to insufficient cure is noticed, the addition of 5 – 10 % BF Mixing Clear will increase light penetration and improve cure. Addition of thinner will not improve cure and may cause the cure rate to decrease. Intensity of cure, weight or caliper of the material as well as elevated ambient temperatures and humidity of the printing and storage environments can influence the block resistance of stacked prints.

* It is the printer's responsibility to pre-test and qualify the parameters, prior to each run.

COVERAGE

Ultrabond BF will yield an average of 3600 to 3800 sq. ft. per gallon based on film deposit of 0.40 to 0.60 mil, dependent on color and printing conditions.

SQUEEGEE

A 70-90 Durometer polyurethane blade is recommended.

INK MODIFICATION

BF Mixing Clear may be added to reduce opacity thus increasing cure speed. BF Mixing Clear is not recommended for viscosity reduction. UV Universal Thinner is recommended for viscosity reduction. It is not recommended to exceed 10% by total weight as this will reduce cure rate and may affect adhesion.

LIGHT FASTNESS

At full strength and fully cured, BF Series ink has been formulated to withstand 2-3 years of exterior exposure. The use of Overprint Clear will increase the inks outdoor durability. Factors beyond our control that may negatively impact the outdoor durability expectations include but are not limited to: substrate grade/age, poor cure of ink film, directional positioning, ink film deposit, exposure to excessive abrasives and air pollutants.

METALLICS

BF Metallic Mixing Clear is supplied for use in mixing metallic powders and pastes. The increase in viscosity of Metallic Mixing Clear helps insure a good particle suspension and maintain a good premix shelf life. The recommended mixing ratios are 8% by weight of silver powder and 20% of gold powder or 12% of silver paste and 28% of gold paste. For optimum coverage and opacity, 280-305 meshes are recommended. With the use of BF Overprint Clear, extended weatherability and improved non-tarnishing properties can be achieved.

COLOR AVAILABILITY

Ultrabond BF is available in twenty standard opaque colors and nine Color Matching System shades. Inktech's Color Formulating Guide reproduces over 1,000 colors utilizing the CMS shades. Custom matches, fluorescent, metallic and transparent colors are available upon request.

STANDARD COLORS

BF-0101 Primrose Yellow	BF-0205 Reflex Blue
BF-0111 Lemon Yellow	BF-0225 Forest Green
BF-0123 Medium Yellow	BF-0226 Lime Green
BF-0131 Brilliant Orange	BF-0210 Ultra Blue
BF-0135 Vivid Orange	BF-0220 Emerald Green
BF-0141 Fire Red	BF-0235 Teal
BF-0151 Scarlet Red	BF-0240 Purple
BF-0155 Rubine Red	BF-0260 Brown
BF-0160 Rhodamine Red	BF-0301 Opaque Black
BF-0180 Warm Red	BF-0311 Opaque White
BF-0190 Process Blue	BF-1350 Overprint Clear
BF-0200 Peacock Blue	BF-1710 Metallic Mixing Clear
UV -1800 Thinner	

COLOR MATCHING SYSTEM COLORS

BF-0064 CMS GS Yellow
BF-0066 CMS RS Yellow
BF-0114 CMS Orange
BF-0121 CMS YS Red
BF-0164 CMS BS Red
BF-0165 CMS Magenta
BF-0127 CMS Violet
BF-0230 CMS Blue
BF-0325 CMS Green
BF-0110 Shading Black
BF-0112 Tinting White
BF-1700 Mixing Clear

PROCESS COLORS

Ultrabond BF four color process colors exceed "SWOP" standards. Variation in densities may be achieved with the use of BF Halftone Base.

	High Density	Back-lit Density
BF-Halftone Yellow	1.10	1.35
BF-Halftone Red	1.75	2.05
BF-Halftone Blue	1.80	2.20
BF-Halftone Black	2.00	2.25
BF-Halftone Extender Base		

FLUORESCENT COLORS

Ultrabond BF is available upon request in nine shades of fluorescent colors. Fluorescent pigments are not light stable. For maximum brightness and color stability, 260 – 305 mesh count is recommended.

BF-0900 Magenta	BF-0940 Chartreuse	BF-0970 Pink
BF-0910 Orange/Red	BF-0950 Red	BF-0980 Orange
BF-0920 Green	BF-0960 Orange/Yellow	BF-0990 Blue

CAUTION:

Read Material Safety Data Sheet prior to using.

End user must determine suitability of this product for the intended use prior to production.

Always premix prior to use.